



表裏両面にインキとの密着性を上げる易接着処理を施した印刷用の超透明PETフィルム
 High transparent PET film for printing with easy adhesive process on both sides.

TEST		UNIT	METHOD	RESULT				
厚み Base Film Thickness		μm	-	100	125	188	250	
ヘイズ Haze		%	JIS K7136	0.9	0.8	0.9	0.9	
全光線透過率 Transmittance		%	JIS K7361	90.3	91.0	90.3	90.8	
引張強度 Tensile Strength	MD	MPa	JIS C2318	225	226	194	181	
	TD			271	262	244	236	
伸び率 Tensile Elongation	MD	%		145	151	147	149	
	TD			93	97	96	93	
加熱収縮率 Thermal Shrinkage	MD	%		JIS C2318 150°C×30min	0.9	0.9	0.8	0.8
	TD				0.4	0.6	0.7	0.7
静摩擦係数 Coefficient of Friction		-	JIS K7125	0.5	0.5	0.5	0.5	
動摩擦係数 Kinetic Coefficient of Friction		-	JIS K7125	0.5	0.5	0.5	0.5	

* 上記データはいずれも代表値です。It is not warranty spec.

▶ 構成/Structure

易接着層 / Easy Adhesion for Printing etc.

PET

易接着層 / Easy Adhesion for Printing etc.